

# AKSAD GROUP PETROCHEM

## ABS-50

### Application

Electronic and Electrical parts, vacuum cleaner, washing machine cover and Refrigerator door cap & etc

### Classification

General purpose

### Characteristic

Medium Impact, High rigidity

Property	Test method	Test condition	Unit	Typical value	ABS-50 specificatio
Izod impact	D-256	6.4 mm , notched	Kj/m <sup>2</sup>	23	Min19
Melt flow index	D-1238	220°C , 10 kg	gr/10 min	35	29-39
Rock well hardness	D-785	.....	R-scale	109	95-115
HDT	D-648	1.82 m pa	°c	85	Min82
Vicat softening Temp	D-1525	5kg/50°C	°c	95	Min 93
Tensile strength	D-638	23°C , 50 mm/min	Kg/cm <sup>2</sup>	455	Min420
Tensile elongation	D-638	23°C , 50 mm/min	%	20	Min 16
Flexural strength	D-790	23°C , 2.8 mm/min	Kg/cm <sup>2</sup>	650	Min 620
Flexural Modulus	D-790	23°C , 2.8 mm/min	Kg/cm <sup>2</sup>	22000	Min17000
Specific Gravity	D-792	23°C	..	1.04	1.04
Molding Shrinkage	D-955	...	%	0.4-0.7	0.4-0.7
Flammability	UI94	1/8inch(3.2mm)	..	HB	HB

### TYPICAL ABS PROCESSING CONDITIONS

#### DRYING:

it is recommended that GBPC ABS Resins be dried at (80-85°C)for 3 hours.

The following molding conditions are recommended starting point for GBPC ABS Resin. A moisture level of ≤0.1% should be reached before injection molding the resin.

Some modifications may be required depending on the specific molding equipment and part configuration

#### INJECTION MOLDIN

Rear Temp(°c)	Center Temp (°c)	Center Temp (°c)	Front Temp (°c)	Nozzle Temp (°c)	Melt Temp (°c)
190-200	200-210	210-220	210-220	215-225	230

Commercial Manager cell phone: +98- 912 127 45 75