

AKSAD GROUP PETROCHEM

SBR-1712

Application

Tire treads, Cameback, Hoses general range of black industrial products

Properties	Volatile Matter	Ash	Organic Acid	Soap	Bound Styrene	Raw Viscosity (ML 1+4@100C°)	Compound Viscosity (ML 1+4@100C°)	Tensileensile Vicosits	Ultimate Elongation (35 minutes cures)	300% Moudulus (35 minutes cures)
Method	ASTMD-1416	ASTMD-1416	ASTMD-1416	ASTMD-1416	ASTMD-1416	ASTMD-1646	ASTMD-1646	ASTMD-412	ASTMD-412	ASTMD-412
Value	0.75 max	1.50 max	3.90-5.70	0.5max	22.5-24.5	42-52	62 max	200 min	530 min	79-109
Unit	Wt. %	Wt. %	Wt. %	Wt. %	Wt. %	-	-	Kg/cm2	%	Kg/cm2

Commercial Manager cell phone: +98- 912 127 45 75